

Description: Flexible barrier Film

Product: SEAL PLUS BEIGE & BLACK 80 μ

This TDS is valid from the production date: 11/04/2018

TEST		U.M.	METHOD	TYPICAL VALUE (^)
Thickness		μ	ISO 4593	80 \pm 10%
Weight		gr/sqm	Internal	78 \pm 10%
Tensile strenght at break	MD	MPa	ASTM D882	45 \pm 15%
	TD	Mpa	ASTM D882	40 \pm 15%
Elongation at break	MD	%	ASTM D882	880 \pm 15%
	TD	%	ASTM D882	800 \pm 15%
Dart Drop Test		(wheight) g	ASTM D1709 method A	1060 \pm 15%
Dart Drop Test		(wheight) g	ASTM D1709 method B	700 \pm 15%
Puncture Properties		N	ASTM F 1306	15 \pm 10%
		mm		17 \pm 10%
Tear Strength	MD	N	Elmendorf Method ISO 6383-2 (Parte 2)	10 \pm 30%
	TD	N		30 \pm 30%
Oxygen Transmission Rate		Cm ³ /m ² /d * (@23°C, 0% RH) 100% O ₂ (1,0 bar)	ASTM D3985-02	4 \pm 15%
		Cm ³ /m ² /d * (@23°C, 0% RH) 20% O ₂ (0,2 bar)	DIN 53380	0,8 \pm 15%
		Cm ³ /m ² /d * (@23°C, 50% RH) 100% O ₂ (1,0 bar)	ASTM D3985-02	3 \pm 15%
		Cm ³ /m ² /d * (@23°C, 50% RH) 20% O ₂ (0,2 bar)	DIN 53380	0,6 \pm 15%
UV Resistance		approximately 140 Kly 12 Months life depends on the area of exposure **		

** Guaranteed till to a decay of 50% of the Mechanical Properties and Oxygen Transmission Rate.

(^) All mechanical test done @23°C, 50%RH.

The obtained values don't derive from a single point but from the averaging obtained by all the batch.

Storage:

Temperature: -10°C + 30°C (time extended storage at high temperature, above 35°C, may cause blocking problems, compromising the unwinding).

Avoid direct exposition to sunrays (time extended exposition to UV may cause a loss in mechanical properties).

Quality Manager

Orazio Polello

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract, nor to constitute any warranty or representation as to quality or fitness for purpose. All products are sold subject to the 2 Gamma Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.